

## Product Code **SL-100HT**

**BASE CLOTH:** 185CM 100D AIR TEXTURED POLYESTER DPP  
**SPECIAL FINISHES:** PRINTED PU COATED  
**REFERENCE GUIDE:** PRE DYED KHAKI BASECLOTH  
 DEF(AUST)8264 ISSUE 1 ITEM 2

TEST	METHOD	REQUIREMENT	RESULTS
MASS	AS 2001.2.13	UNDER 100G/M2	98G/M2
BREAKING FORCE	AS 2001.2.3.1	LENGTH 650N WIDTH 520N	1000N 820N
BREAKING FORCE AFTER AGEING	AS 2001.4.21	RETAIN 50% STRENGTH	WARP 58% WEFT 51%
TEAR RESISTANCE	AS 2001.2.10	WARP 18N WEFT 15.5N	28N 25N
COLOR FASTNESS TO LIGHT (ARTIFICIAL)	AS 2001.4.B02	6	6
COLOR FASTNESS TO WATER	AS 2001.4.E01	4-5	4-5
COLOR FASTNESS TO RUBBING	AS2001.4.3	DRY 3-4 WET 3-4	4-5 4-5
HEAT AGEING (BLOCKING)	AS 4878.11	NO GREATER THAN 2	LESS THAN 2
YARN SLIPPAGE	AS 2001.2.22	WARP 3MM WEFT 3MM	BELOW 3MM BELOW 3MM
FLEX ABRASION	AS 2001.2.26	6000 CYCLES	6000 PLUS
WATER REPELLENCY	AS 2001.2.16	80	100 (5)
WATER RESISTANCE	AS 2001.2.17	50KPA	200 KPA
WATER PENETRATION	AS 2001.2.18	ZERO LEAKAGE	ZERO LEAKAGE
PH VALUE	2001.3.1 B	5-8	6.4

### DISCLAIMER

The information contained in the product Data Sheet is based on results obtained on the sample assessed at the time in accordance with the method provided. The values are a guide to purchasers of the Fabric to evaluate the Fabric and determine its suitability for their products intended end use

**SPEEDLINE TEXTILES P/L**  
**C/- Storage King Dandenong Bld**  
**7/22 Carter Way**  
**Dandenong South Vic 3175**

**Ph [03] 9702 7563**  
**Fax [03] 9702 7564**

**speedlinetextiles@gmail.com**  
**Robert Krivaci – Mobile 0417 244 004**